

Application No.: 10/509,156  
Art Unit: 1793

Amendment under 37 C.F.R. §1.111  
Attorney Docket No.: 042724

**AMENDMENTS TO THE SPECIFICATION**

**Please replace Table 1 on page 11 as follows:**

(Table 1)

	Pure Mo	Material subjected to internal nitriding up to third step	(Internal nitriding up to third step) + (external nitriding) (2.8 $\mu$ m)
Yield strength	550 MPa	1190 MPa	1280 MPa
Maximum strength	750 MPa	<del>1020 MPa</del> <u>1620 MPa</u>	1870 MPa